

CARLEATHER

Origin: South American hides

Tanning: Italy Colour range: 31

Thickness: 1.1 mm - 1.3 mm

Chrome tanning Corrected grain

Description:

Carleather is produced by one of the most well known tanneries in the automotive market that deliveres directly to the car brands. This gives us the big advantage that Carleather is produced in the same way and standards as the leather used by the automotive brands.

Technical aspects:

Lightfastness: DIN 75202 Min 4 – 5 blue scale

Abrasion resistance: IUF 450

Dry: 2000 cycles > 4 - 5 grey scale

Wet: 500 cycles > 4 - 5 grey scale

Taber: ASTM D-1175 500 cycles : pass

Tear strength: IUP 8 > 15 N/mm

Adhesion of the finish: IUF 470 > 3 N

Flexing endurance: EN ISO 5402 25 000 cycles

Fogging: DIN 75201 < 7 mg

Fire retardancy: FMVSS 302