

Paloma

Technische fiche

Oorsprong	oostenrijkse huiden	
Vering	vatgeverfd	
Looing	chrroomgeloid	
Finish	softy finish	
Oppervlakte	naturel - volnerf	
Dikte	0,9/1,1 mm	
Inspection characteristics	Standard	Requirements
Tensile strength	DIN 53328	≥ 800 N/cm ²
Elongation at break	DIN 53328	30 - 70 %
Tear resistance	DIN 53329	20 N/mm
Flexometer	DIN 53351	20.000 : no damage to finish
Light fastness	DIN 54004	≥ 4
Fastness to rubbing	DIN 53339	500 dry 80 wet 50 pH9 felt: ≥ 4 no damage to finish
pH-value	DIN 53312	$\geq 3,5$
Adhesion of finish	IUF 470	$\geq 1,5$ N/cm